

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): A cured material, obtained by irradiating a curable resin composition with an active energy ray so that a moiety of a polymer block A contained in the curable resin composition is crosslinked, the curable resin comprising, an addition polymerization-based block copolymer (I), ~~and an ethylenic unsaturated compound (II), and a~~ photopolymerization initiator (III), wherein:

the addition polymerization-based block copolymer (I) is selected from block copolymers comprising at least one polymer block A and at least one polymer block B, and the hydrogenated products thereof;

the polymer block A ~~essentially~~ comprises an aromatic vinyl compound unit containing ~~at least 1%~~ at least 10% by mass of an alkylstyrene-derived structural unit (a) in which at least one alkyl group having 1 to 8 carbon atoms is bound to a benzene ring; and

the polymer block B ~~essentially~~ comprises a conjugated diene compound unit; ~~and~~
~~at least the moiety of polymer block A can undergo crosslinking upon exposure to an active energy ray.~~

Claim 2 (Cancelled)

Claim 3 (Currently Amended): The ~~curable resin~~ cured material composition according to claim 1, further comprising a softener (IV).

Claim 4 (Currently Amended): The ~~curable resin~~ cured material composition according to claim 1, wherein the structural unit (a) in which at least one alkyl group having 1 to 8 carbon atoms is bound to a benzene ring is a p-methylstyrene unit.

Claim 5 (Currently Amended): A flexographic plate material, comprising the ~~curable~~
~~resin composition~~ cured material according to claim 1 as a constituent.